
Product data **Laminate flooring** Classic

LC 75



	Tests	DIN/EN standard	Laminate flooring Classic LC 75
Seneral data o	n product composition		
	Type of covering:		Flooring panel with top layer made from specially-resined decor paper
	Total thickness:		approx. 8mm
	Effective measurement: (length × width)		1288 x 198mm
	Product structure:		a. Overlay b. Decorative paper c. HDF base board (approx. 890 kg/m 3 \pm 3%) d. Backing
echnical data			
	Locking method:		Multiclic
	Wear class:	EN 13 329	23 32
	Wear resistance:	EN 13 329 (appendix E)	AC4 (= IP ≥ 4,000 U)
Ô	Impact resistance:	EN 13 329 (appendix F)	IC 2
	Stain resistance:	EN 13 329 (EN 438-2/26)	Group 1: grade 5 Group 2: grade 5 Group 3: grade 4-5
*	Colour fastness:	EN 13 329 (EN ISO 105)	≥ stage 6 on the blue wool scale
C _{fl} -s1	Fire behaviour:	EN 13 501	C _{fl} -s1 (hardly flammable)
OS SO	Slip resistance:	EN 14 041 / 13 893	DS
	Scratch resistance:	EN 438-2/25	≥ 5 N
Е1	Formaldehyde emissions (E1 = 0.1 ppm):	EN 717-1	≤ 0.05 ppm
	Indent after constant load:	EN 13 329 (EN 433)	no visible changes

10|16

	Castor resistance:	EN 425	no visible changes or damage with soft, standard castors
	Behaviour on simulation of shifting furniture foot:	EN 13 329 (EN 424)	no visible damage
	Underfloor heating:		Suitable for hot-water underfloor heating Electrical underfloor heating is generally suitable when it is built into the floor screed or the concrete layer and thus does not lie on the concrete layer as foil heating. The heating elements pipes wires must lie across the entire area and not just be partly present. If the area is only partially heated, the floor covering must have expansion joints (system profile strips). The maximum permitted surface temperature is 29°C. Standard foil heating systems are generally not recommended. One exception is self-regulating heating systems which maintain the 29°C surface temperature.
	Heat transfer resistance:	EN 12 667	with MEISTER-Silence 25 DB: 0.07 m ² K/W
olerances			
	Right-angle of the elements:	EN 13 329	target values met
	Determination of edge straightness:	EN 13 329	target values met
	Surface flushness:	EN 13 329	target values met
	Joint opening between the elements:	EN 13 329	target values met
eneral data	on environment, installation and c	are	
	Blue Angel:	RAL-UZ 176	awarded
	Disposal:		Residual pieces can be disposed of in household refuse (e.g. thermal treatment) Dispose large quantities according to municipal provisions (e.g. recycling centres) An energetic utilization in authorized plants is recommended.
	Cleaning and care:		Cleaning after construction work/ day-to-day cleaning: CC Laminate Cleaner Special cleaning: CC-Elatex Stain Remover
	Areas of application:		The Classic flooring LC 75 is suitable for all living areas as well as for commercial areas with normal wear. e. g. offices, waiting rooms, boutiques etc. This flooring is not suitable for installing in humid rooms (bathrooms, saunas, etc.). Special requirements apply to treatment rooms and medical practices.
	Preconditions for installation:	DIN 18 365	The substrates must be ready for laying on according to the generally recognised rules of the trade, taking into account VOB (German construction contract procedures), part C DIN 18 365 "parquetry work". The substrate must be dry (in the case of mineral substrates max. 2% or with underfloor heating 1.8 %, with anhydrite screed max. 0.5% or with underfloor heating 0.3 % residual moisture – measured with CM devices) even, firm and clean. Additionally, any unevenness of 3mm/ per initial metre and 2mm per further metre must be evened out according to DIN 18 202, table 3, line 4.The installation instructions provided with the product must be observed.













MeisterWerke Schulte GmbH reserves the right to make alterations to material and structures when this serves to improve the quality.

10|16